NO. :



APPROVAL SHEET

MULTILAYER CERAMIC CAPACITOR Commercial Grade (High Voltage Type (100V~3000V))

Approved by customer : (signing or stamping here)

SAM	WHA CAPACITOR CO	., LTD.
Writtern by	Checked by	Approved by
2485	for	The

2020. 02. 13.



Address : 124, BUK-RI, NAMSA-MYUN YOUNGIN-SI, KYUNGKI-DO, KOREA Contact : TEL 82-31-332-6441 , FAX 82-31-332-7661 Home page : www.samwha.com

	< SPE	EC S	UMMARY >
SAMWHA Part no.		CS3	3216X7R225K101NRI
Туре			High voltage
Item	Specification	Unit	Test methods and Conditions(Capacitance,IR)
Capacitance	2.2	μF	
Capacitance Tolerance	± 10	%	Testing Frequency: 1 ±0.2kHz Testing Voltage : 1 ±0.2Vrms
Dissipation Factor	Max. 5	%	
Insulation Resistance	More than 45,4	MΩ	Applied the rated voltage for 2 minutes of charging.
	3.20 ±0.30	L (mm)	-*Capacitance Tolerance Code page 1/9
Chip Size	1.60 ±0.30	W (mm)	*Chip size page 2/9
	1.60 ±0.30	T (mm)	- *Characteristics & Test Method page 3/9~6/9

Enactment :			ST	ANDA	RD			NO	S	SW - M	- 0
	h 27,1996	MULT	ILAYER	CERAMI	C CA	PACITO	R	Dam	_	/	0
			Comr	mercial	Grade			Page	Э	1 /	9
These s used to <u>*Caution</u> 2. General	on Range pecifications re the compute <u>n : Industrial e</u> <u>Please cor</u> <u>(For details,</u> Code e Designation	r equipment / equipment / ntact sales please refer	'Multilayer at, comm <u>/ For the</u> represent · Page 9)	Ceramic unication <u>high reli</u> tatives o	capa equip ability r produ	citors "m ment. equipme uct engir	ent / LE neers b	efore usii			<u>ts.</u>
	\underline{CS}	<u>3216</u>	<u>X7R</u>	<u>225</u>	<u>K</u>	<u>101</u>	$\frac{N}{(7)}$	$\frac{\mathbf{R}}{\mathbf{R}}$	<u> </u>		
	(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)		
2) Si		is is expre e first two		ens of a			two di	gits are	width.		
	Th	e first two	digits ar	ens of a	a millin		two di	gits are	width.		
	Th Th	e first two efficient C	digits ar	ens of a e the ler	a millin ngth, 1			gits are Capacita		olerance	
	Th Th emperature Co	e first two efficient Co n C	digits ar ode	ens of a e the ler Tem	a millin ngth, 1	The last re Rang		Capacita			2
	Th Th emperature Co Classificatior	e first two efficient C n C	digits ar ode Code	ens of a e the ler Tem	a millin ngth, 1 nperatu	Fhe last re Rang +125℃		Capacita ±30	nce T		2
	Th Th emperature Co Classificatior	e first two efficient Co n C ()	digits ar ode Code COG	ens of a e the ler Tem	a millin ngth, 1 nperatu -55 to -	rhe last re Rang +125℃ +85℃		Capacita ±3(nce T 0 ppm,		2
	Th Th Classification Class I	e first two efficient C C C C C C C C C C C C C C C C C C C	digits ar ode Code COG K5R	ens of a e the ler Tem -	a millin ngth, 1 nperatu -55 to -55 to	re Rang +125℃ +85℃ +125℃		Capacita ±3	nce T 0 ppm, ±15%	℃ /	
 3) Te 4) Ca Ti Ti 	Th Th Th Classification Class I Class I Class II Class II apacitance Co he nominal Ca he first two dig ex) 104 = 10 R denote 8R2 = 8. Capacitance To Code B	e first two efficient C C C C C C C C C C C C C C C C C C C	digits ar ode Code COG (5R (7R (7SV) rads) : Value in nts signific ode olerance	ens of a e the ler Tem	a millin ngth, 1 -55 to -55 to -30 to	The last rre Rang +125°C +85°C +125°C +85°C ed by th d the las Code M	e	Capacita ±30 +229 git numbe denotes the denotes the denotes the denotes the denotes the denotes the de	nce T 0 ppm, ±15% ±15% % ~ -{ ers. he nur	nber of	
 3) Te 4) Ca Ti Ti 	Th Th Th Classification Class I Class I Class II Class II apacitance Co he nominal Ca he first two dig ex) 104 = 10 R denote 8R2 = 8. apacitance To Code	e first two efficient C n C ()) de(Pico fa apacitance its represer 0000 pF s decimal 2 pF lerance Cc	digits ar ode Code COG K5R K7R Y5V rads) : Value in nts signific ode olerance 1 pF 25 pF	ens of a e the ler Tem	a millin ngth, 1 -55 to -55 to -30 to	The last rre Rang +125°C +85°C +125°C +85°C ed by th d the las	e	Capacita ±30 +229 git numbe denotes t denotes t	nce T 0 ppm, ±15% ±15% % ~ -{ ers. he nur	mber of	

F

G

J

Κ

± 1.0 %

± 2.0 %

± 5 %

± 10 %

Н

I

U

V

+ 0.25/-0 pF

+ 0/-0.25 pF

+ 5/-0 %

+ 0/-5 %

SW - M - 04B 2 / 9

6) Voltage Code

v 1	onage	oouc													
	code	6R3	100	160	250	350	500	101	201	251	501	631	102	202	302
	Val	DC	DC	DC	DC	DC	DC	DC	DC	DC	DC	DC	DC	DC	DC
	Vol.	6.3V	10V	16V	25V	35V	50V	100V	200V	250V	500V	630V	1KV	2KV	ЗKV

7) Termination Code

ex) N : Ni-Sn (Nickel-Tin Plate)

A : Ag/Ni-Sn (Ag Epoxy/Nickel-Tin Plate) -> Soft Termination Type

8) Packing Code

ex) R : 7" Reel Type

L: 13" Reel Type

- B : Bulk Type
- 9) Thickness option

Thickne	ss(mm)	Code
t	Tol(±)	oode
1.60	0.30	I

3. Temperature Characteristics

See Page 3/9 (No.7)

4. Constructions and Dimensions

(I) Dimensions

			· ·	L	W	Ţ	(Unit:mm)
				Dime	nsion			
Code	Ler	ngth	Wi	dth	Thicł	ness		
	L	Tol(±)	W	Tol(±)	Т	Tol(±)	T1(min)	G(min)
3216	3.20	0.30	1.60	0.30	1.60	0.30	0.15	1.00

(2) Construction of Termination



SW - M - 04B 3 / 9

Specifications and Test Methods (High voltage type)

		Spe	ecification						
No.	ltem	Class I	Class II			Test Meth	nods	and Conditions	;
1	Operating Temperature Range	C0G :-55 to+125℃	X7R : −55 to +125℃						
2	Dimensions	Within the specified dimen	sion	Using	cali	pers			
3	Dielectric Strength	No defects or abnormali	ties	betwee is less Cap.	n th thai DC DC DC		provid 150% 120%	when voltage in table ded the charge/discl Test voltage of the rated voltage of the rated voltage of the rated voltage	Time
				X7R	DC	1kV 2kV 3kV	120%	of the rated voltage	;
4	Insulation Resistance	More than 10,000 MΩ	-DC100V~1KV :C≥0.01µF:More than 100MQµF :C<0.01µF:More than 10,000MQ -DC2~3KV:More than6,000 MQ	2 mir Ratec	nute I vo easu	es of charging oltage ≥DC500	g. ov : -	Applied the rated The insulation resis V and within 2 mi	ance should
5	Capacitance	within the s	specified tolerance	Сар)	Testing freque	ncy	Testing Voltage	Measure temperature
		C0G Char. : 30pFmin		C00 X7F	ż	1±0.2Mb(C<10 1±0.1kbc(C≥10 1±0.2kbc		AC 1±0.2Vrms	25℃
6	Dissipation Factor(D.F.)	: Q≥1,000(DF≤0.1%) 30pFmax : Q≥400+20C (DF≤1/ (400+20C))	5% max	Perfo accor • Meas Take	rm din ure it c	easurement the initial mea g to Note1 fo ment after tes out and set it ours (Class II)	r Clas st for 2	ss II 4±2 hours (Class	l) or
		Temp. Coefficient		capac When throug	itan cyc h 5 nce Si	ice measured i cling the tempe	n ster rature ce sh	cient is determined o 3 as a reference sequentially from ould be within the coefficient. Temperature(°C) 25±2	step 1
7	Capacitance Temperature Characteristics	COG char. : 0±30ppm/℃ (Temp. Range : -55to+125℃)	Cap. Change within ±15% (Temp. Range : -55 to +125℃)			2 2 3 4 5 5		-55±3 25±2 125±3 (for COG) 25±2	
				25°Cva -Pretro Perfo 60±5	alue eatr irm imir	should be wit ment a heat treatme	hin th ent at sit fo	nce change compa e specified range. 150 -10, +0°C for or 24±2hrs.(Class Temperature	

			Specifi	cation	
No.	lt	em	Class I	Class II	Test Methods and Conditions
8	Adhesive Stre Termination	ngth of	No removal of the terminations	s or other defect should	Solder the capacitor to the testing jig(glass epoxy board) shown in Fig. 1 using a eutectic solder. Then apply 10N force in the direction of the arrow. The soldering should be done either with an iron or using the reflow method and should be conducted with care so that the soldering is uniform and free of defects such as heat shock. 10N(5N:Size 1.6×0.8mm only), 10±1s Speed : 1.0mm/s Glass Epoxy Board
		Appearance	No defects or abnormalities	3	
		Capacitance	Within the specified tolerance		The capacitor should be subjected to a simple harmonic
9	Vibration Resistance	Dissipation Factor(or Q)	COG Char. : 30pFmin : Q≥1,000(DF≤0.1%) 30pFmax : Q≥400+20C (DF≤1/ (400+20C))	5% max	motion having a total amplitude of 1.5mm, the frequency being varied uniformly between the approximate limits of 10 and 55Hz. The frequency range, from 10 to 55Hz and return to 10Hz, should be traversed in approximately 1 min. This motion should be applied for a period of 2hrs. in each 3mutually perpendicular directions(total of 6hrs.)
			No cracking defects should	occur.	Solder the capacitor to the testing jig (glass epoxy board) shown in Fig. 2 using a eutectic solder. Then apply a force in the direction shown in Fig. 3.
10	Bending stren	gth	(mm) a 1.6×0.8 1.0 3 2.0×1.25 1.2 2 3.2×1.6 2.2 5 3.2×2.5 2.2 5 4.5×2.0 3.5 7	4.5 mension(mm) b c d 3.0 1.2 4.0 1.65 5.0 2.0 5.0 2.9 7.0 2.4 7.0 3.7 1.0	The soldering should be done either with an iron or using the reflow method and should be conducted with care so that the soldering is uniform and free of defects such as heat shock.
11	Solderability c Termination	of	75% of the terminations a and continuously.		Immerse the capacitor in a solution of ethanol and rosin(25% rosin in weight proportion). Immerse in eutectic solder solution for 2±0.5 sec. at 245±5℃. Immersing speed : 25±2.5mm/s

			Spe	cification					
No.	lt	em	Class I	Class II	T	est Method	ls and	I Conditions	
		Appearance	No defects which may	affect performance	_			150℃ * for 1 m	
		Capacitance change	within ±2.5%or ±0.25pF (whichever is larger)	within ±10%		e capacitor in r 10±1 sec.	eutect	ic solder solutio	on at
12	Resistance to Soldering Heat	Dissipation Factor (or Q)	COG Char. : 30 _p Fmin : Q≥1,000(DF≤0.1%) 30 _p Fmax : Q≥400+20C (DF≤1/ (400+20C))	5% max	·Initial meas Perform t according ·Measureme	speed:25± surement he initial me to Note1 fo nt after test oom Temperatu	easurer or Clas	ment	
		I.R.	More than 10,000№	-DC100V~1KV :C≥0.01µF:More than 100MΩ·µF :C<0.01µF:More than 10,000MΩ -DC2~3KV:More than1,000 MΩ		for more tha	n 3.2× erature o 120℃	Time 1 mii	e n
		Appearance	No defects which may	affect performance	Porform the		ording	to the 4 heat tr	ootmon
		Capacitance Change	Within ±2.5%or ±0.25pF (whichever is larger)	within ±15%	listed in the	following tab	le.		
13	Temperature	Dissipation Factor	C0G Char. : 30pFmin : Q≧1,000(DF≦0.1%) 30pFmax	5% max	(°C) te	mp. ±3 1	2 Room Temp 2 to3	3 Max. operating temp. ±2 30±3	4 Room Temp 2 to3
10	Cycle	(or Q)	: Q≥400+20C (DF≤1/ (400+20C))					ment accordir	ng
		I.R	More than 10,000MQ	-DC100V~1KV :C≥0.01µF:More than 100MΩ·µF :C<0.01µF:More than 10,000MΩ -DC2~3KV:More than 3,000MΩ	·Measureme	nt after test		ent according	J
		Appearance	No defects which may	affect performance					
		Capacitance Change	within ±5% or ±0.5pF (Whichever is larger)	Within ±15%		acitor sit at 40 for 500+24/-0		and relative hur	midity o
14	Humidity (Steady State)	Dissipation Factor (or Q)	$\begin{array}{l} \text{COG Char.:}\\ \text{C} \geqq 30 \text{pF} : \text{Q} \geqq 350\\ \text{C} < 30 \text{pF} : \text{Q} \geqq 275 + \frac{5}{2}/\text{C} \end{array}$	7.5% max	to Note1	the initial m for Class		ement accord	ing
		I.R	More than 1,000MΩ	-DC100V~1KV :C≥0.01μF:More than 10№μF :C<0.01μF:More than 1,000№ -DC2~3KV:More than 1,000№	Perform to Note2			nent accordin	g
		Appearance	No defects which may	affect performance	Apply the v for 1,000+4	oltage in follo	owing ta	able	
		Capacitance Change	within ±3% or ±0.3pF (Whichever is larger)	DC100V,630V:Within ±15% DC1KV:Within ±20% DC2~3KV:Within ±20%	at maximun	n operating te		ture ±3℃. less than 50m.	A.
		Dissipation (or Q)	COG Char. : $C \ge 30 pF$: $Q \ge 350$	7.5% max	Operating temperature range	Rated voltag		Test voltage	
	High		C<30pF : Q \ge 275+ $\frac{5}{2}$ /C		C0G	≥DC1KV Rated voltage		ed voltage % of the rated v	oltage
15	Temperature Load				X7R	<pre><dc1kv dc100v~250v="" dc1kv~dc3k<="" dc500v~630v="" pre=""></dc1kv></pre>	/ 150 [,] / 120 [,]	% of the rated v % of the rated v % of the rated v % of the rated v	oltage oltage
		I.R.	More than 1,000№	-DC100V~1KV :C≥0.01µF:More than 10MQ·µF :C<0.01µF:More than 1,000MQ -DC2~3KV:More than 2,000MQ	to Note1 •Measureme	surement the initial m for Class int after test the final me	ieasure 	ement accord	ing



SW - M - 04B	6/9
--------------	-----

				Specification	
No.		tem	Class I	Class II	Test Methods and Conditions
		Appearance		No defects which may affect performance	Apply the rated voltage at $40\pm2^{\circ}$ and relative
	Humidity Load	Capacitance Change		Within ±15%	humidity of 90 to 95 for 500+24/-0 hrs. Initial measurement
16	(Application : DC250V	Dissipation (or Q)		7.5% max	Perform the initial measurement according to Note1 for Class II
	item)	I.R.		C≥0.01µF:More than 10MQ·µF C<0.01µF:More than 1,000MQ	 Measurement after test Perform the final measurement according to Note2

*Note1. Initial Measurement for Class II

Perform a heat treatment at 150+0,-10°C for one hour and then let sit for 24±2 hours at room temperature, then measure

*Note2. Measurement after test

1.Class I

Let sit for 24±2 hours at room temperature, then measurement

2.Class II

Perform a heat treatment at 150+0,-10°C for one hour and then let sit for 24±2 hours at room temperature, then measure.



	 2 5 Polyb 3 10 Inne 			NY.					
(2) Reel Pac		n noves t							
	① 8~10 F	Poole por	Innor boy						
	2 6 Inner			,					
2) Deel Dim		Doxes he		κ.					
(3) Reel Dim	lensions								(
		MARK	SIZE	Α	В	С	D	E	(Unit : r W
(স্কিঁম)			0603~3225		Φ50Min	Φ13±0.5	Φ21±0.8		
\ SI /j		7 " REEL	4520~4532			Φ13±0.2	Φ57-0+1		
	_ ԼաԼ	13 " REEL	1005~3225	5 Φ330±2	Φ70Min	Φ13±0.5	Φ21±0.8	3 2±0.5	5 10±1
	r i								
(4)Number c	of Package								
				7"			13"		
TYPE		IA CODE		Qt/REEL			Qt/REEL		
CS060 CS100		CC0201 CC0402		15,000			50,000		
CS160		CC0603		4,000			15,000		
CS201		CC0805		3,000 ~ 4,00			000 ~ 15,		
CS321 CS322		CC1206 CC1210		2,000 ~ 4,00 1,000 ~ 3,00			$\frac{000 \sim 10,0}{000 \sim 10,0}$		
CS452		CC1210 CC1808		$\frac{1,000}{1,500} \sim 3,00$		4,	-	000	
CS453	32	CC1812		500 ~ 1,000		1	,500 ~ 5,0	00	
(5) Tape D	imensions					0.3mi	•× (0.4max +	
	Imensions				A			• • • • • • • • • • • • • • • • • • •	
					E			A THE AND AND A THE AND A THE ATHENA AND AND A THE ATHENA AND A THE ATHENA	J
C C C C C C C C C C C C C C C C C C C	P INSERT	A 0.67±0.05	B 0.37±0.05 8	C D .0±0.3 3.5±C	РАРЕ Е .05 1.75±0.1	F 2.0±0.05	G 2.0±0.1	н 4.0±0.1	1.5±0.1
C C C C C C C C C C C C C C C C C C C	P INSERT EIA CODE CC0201 CC0402	A 0.67±0.05 1.15±0.1	B 0.37±0.05 0.65±0.1 8	C D .0±0.3 3.5±0 .0±0.3 3.5±0	PAPE 05 1.75±0.1 05 1.75±0.1	F 2.0±0.05 2.0±0.05	G 2.0±0.1	H 4.0±0.1	1.5±0.1 1.5±0.1
C C C C C C C C C C C C C C C C C C C	P INSERT	A 0.67±0.05	B 0.37±0.05 0.65±0.1 1.10±0.2 8	C D .0±0.3 3.5±C .0±0.3 3.5±C .0±0.3 3.5±C	E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1	F 2.0±0.05 2.0±0.05 4.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1	H 4.0±0.1 4.0±0.1	1.5±0.1
C C C C C C C C C C C C C C C C C C C	P INSERT EIA CODE CC0201 CC0402	A 0.67±0.05 1.15±0.1	B 0.37±0.05 0.65±0.1 1.10±0.2 8	C D .0±0.3 3.5±0 .0±0.3 3.5±0	E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1	F 2.0±0.05 2.0±0.05 4.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1	H 4.0±0.1	1.5±0.1 1.5±0.1
E C C D C C	P INSERT EIA CODE CC0201 CC0402 CC0603	A 0.67±0.05 1.15±0.1 1.9±0.2	B 0.65±0.1 1.65±0.2 8	C D .0±0.3 3.5±C .0±0.3 3.5±C .0±0.3 3.5±C	E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1	F 2.0±0.05 2.0±0.1 4.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1	H 4.0±0.1 4.0±0.1 4.0±0.1	1.5±0.1 1.5±0.1 1.5±0.1
E ↓	J P INSERT EIA CODE CC0201 CC0402 CC0603 CC0805	A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2	B 0.37±0.05 8 0.65±0.1 1.10±0.2 8 1.65±0.2 8 2.00±0.2 8	C D .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0	E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1	F 2.0±0.05 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1	H 4.0±0.1 4.0±0.1 4.0±0.1	1.5±0.1 1.5±0.1 1.5±0.1 1.5±0.1
TYPE CS0603 CS1005 CS1608 CS2012 CS3216	U INSERT ■ INS	A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2 3.6±0.2	B 0.37±0.05 8 0.65±0.1 1.10±0.2 8 2.00±0.2 8 2.80±0.2 8	C D .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0	E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1	F 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1	н 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1	$1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1$
TYPE CS0603 CS1005 CS1608 CS2012 CS3216 CS3225	J P INSERT EIA CODE CC0201 CC0402 CC0603 CC0805 CC1206 CC1210	A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2 3.6±0.2 3.6±0.2	B 0.37±0.05 8 1.10±0.2 8 2.80±0.2 8 2.3±0.2 12	C D .0±0.3 3.5±C	E 05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1	F 2.0 2.0±0.05 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 8.0±0.1 8.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1	H 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1	$1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1$
TYPE CS0603 CS1005 CS1608 CS2012 CS3216 CS3225 CS4520	U U U U U U U U U U U U U U	A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2 3.6±0.2 3.6±0.2 4.8±0.2	B 0.37±0.05 8 1.10±0.2 8 2.80±0.2 8 2.3±0.2 12	C D .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0	E 05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1	F 2.0 2.0±0.05 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 8.0±0.1 8.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1	H 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1	$1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1$
TYPE CS0603 CS1005 CS1608 CS2012 CS3216 CS3225 CS4520	U U U U U U U U U U U U U U	A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2 3.6±0.2 3.6±0.2 4.8±0.2	B 0.37±0.05 8 1.10±0.2 8 2.80±0.2 8 2.3±0.2 12	C D .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 5.5±0	E 05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1	F 2.0±0.05 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 8.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1	H 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1	$1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm$
TYPE CS0603 CS1005 CS1608 CS2012 CS3216 CS3225 CS4520	EIA CODE CC0201 CC0402 CC0603 CC1206 CC1210 CC1808 CC1812	A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2 3.6±0.2 4.8±0.2 4.9±0.2	B 0.37±0.05 8 0.65±0.1 1.10±0.2 8 2.00±0.2 8 2.3±0.2 12 3.6±0.2 12	C D .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 5.5±0 2.0±0.3 5.5±0	E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .01 1.75±0.1	F 2.0±0.05 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 8.0±0.1 8.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1	H 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1	$1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1$
TYPE CS0603 CS1005 CS1608 CS2012 CS3216 CS3225 CS4520 CS4532	U INSERT ■ INS	A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2 3.6±0.2 4.8±0.2 4.9±0.2	B 0.37±0.05 8 0.65±0.1 1.10±0.2 8 2.00±0.2 8 2.3±0.2 3.6±0.2 12 3.6±0.2 12 3.6±0.2 12	C D 0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 5.5±0 2.0±0.3 5.5±0	E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .01 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1	F 2.0±0.05 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 8.0±0.1 8.0±0.1 8.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 DER	H 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1	$1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm0.1$
TYPE CS0603 CS1005 CS1608 CS2012 CS3216 CS3225 CS4520 CS4532	J ■ <t< td=""><td>A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2 3.6±0.2 4.8±0.2 4.9±0.2</td><td>B 0.37±0.05 8 0.65±0.1 1.0±0.2 8 2.00±0.2 8 2.80±0.2 8 2.80±0.2 8 2.3±0.2 12 3.6±0.2 12 3.6±0.2 12 CHIPS</td><td>C D 0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 5.5±0 2.0±0.3 5.5±0 </td><td>E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .01 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1</td><td>F 2.0±0.05 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 8.0±0.1 8.0±0.1 8.0±0.1</td><td>G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 DER</td><td>H 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1</td><td>$1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm$</td></t<>	A 0.67±0.05 1.15±0.1 1.9±0.2 2.4±0.2 3.6±0.2 4.8±0.2 4.9±0.2	B 0.37±0.05 8 0.65±0.1 1.0±0.2 8 2.00±0.2 8 2.80±0.2 8 2.80±0.2 8 2.3±0.2 12 3.6±0.2 12 3.6±0.2 12 CHIPS	C D 0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 3.5±0 .0±0.3 5.5±0 2.0±0.3 5.5±0	E .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .05 1.75±0.1 .01 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1 .1 1.75±0.1	F 2.0±0.05 2.0±0.05 2.0±0.05 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 8.0±0.1 8.0±0.1 8.0±0.1	G 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 2.0±0.1 DER	H 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1 4.0±0.1	$1.5\pm0.1 \\ 1.5\pm0.1 \\ 1.5\pm$

SW - M - 04B

7 / 9


5. Packing


6.Caution

- ► Reflow Soldering
- 1. The sudden temperature change easily causes mechanical damages to ceramic components. Therefore, the preheating procedures should be required for the soldering of ceramic components.
- Please refer to the recommended soldering profiles as shown in figures, and keep the temperature difference(△T) within the range recommended in Table 1.

Table 1

Size code	Temperature Difference
0603, 1005, 1608, 2012, 3216	∆T≤190℃
3225size and over	∆T≤130℃





In case of repeated soldering, the accumulated soldering time must be within the range shown above.

► Storage Condition


*When Solderability is considered, Capacitor are recommended to be used in 12 months

- (1) Temperature: $25^{\circ}C \pm 10^{\circ}C$
- (2) Relative Humidity: Below 70% RH
- ► The Regulation of Environmental Pollution Materials.

*Never use materials mentioned below in MLCC products regulated this document.

Pb, Cd, Hg, Cr^{+6} , PBB(Polybromide biphenyl), PBDE(Polybrominated diphenyl ethers), asbestos.

	SW - M - 04B	9/9
 Note (1) 'Aging'/'De-aging' Behavior of high dielectric MLCCs (Typically represented by X7R, Y5V temperature characteristic of w 	hich main composition is	BaTiO3)
'Aging' / 'De-aging' Behavior of high dielectric MLCCs Please note th Ceramic Capacitors have a "normal" 'aging' behavior / characteristic, value decreases with time from its value when it was first manufactur capacitance value begins to decrease at a logarithmic rate defined b	that is; their capacitance red. From that date, the	
$C_t = C_{24} (1 - k \log 10 t)$		
where :		
Ct = Capacitance Value, t hours after the start of 'aging' C ₂₄ = Capacitance Value, 24 hours after its manufacture k = aging constant (capacitance decrease per decade-hour) t = time, in hours, from the start of 'aging'		
Ceramic's Capacitance Change (%) versus Tin	ne (Hours)	



The capacitance value can be restored (a.k.a. 'de-aged') by exposing the component to elevated temperatures approaching its Curie Temperature (approximately 120°C). This 'deaging' can occur during the component's solder-assembly onto the PCB, during life or temperature cycle testing., or by ' baking ' at 150°C for about 1 hour.