

Prosperity Dielectrics Co., Ltd.

No.566-1, Kaoshi Rd., Yangmei, Taoyuan 32668, Taiwan (R.O.C.)

Tel : 886-3-4753355

Fax : 886-3-4854959

Messrs. : 一般共用

Date : 2022/07/06

APPROVAL SHEET

Product Name : Stacked Capacitors

Part No. : FE Series

Description : Size 1210~2225, C0G/X7R, 50~630Vdc

PREPARED BY	APPROVED BY

信昌電子陶瓷股份有限公司

PROSPERITY DIELECTRICS CO., LTD.

桃園市場梅區高獅路 566-1 號 <http://www.pdc.com.tw>

Tel : 03-4753355 ext :

Fax : 03-4854959

Contactor : _____ **Mobile :** _____

Prosperity Dielectrics Co., Ltd.

No.566-1, Kaoshi Rd., Yangmei, Taoyuan 32668, Taiwan (R.O.C.)

Tel : 886-3-4753355

Fax : 886-3-4854959

SPECIFICATION

FOR

Product Name : Stacked Capacitors

Part No. : FE Series

Description : Size 1210~2225, C0G/X7R, 50~630Vdc

SPEC. No. : FE-000-001-13

DATE : 2022/07/06

DRAWN BY	CHECEKED BY	APPROVED BY
<i>Jane Hsiao</i>	<i>Yvens Chou</i>	<i>Jason Lin</i>

1. INTRODUCTION

FE Series green type capacitors are manufactured by using green materials without lead and cadmium. These capacitors to achieve a unique structure of high reliability. The use of metal lead frame, can absorb the heat and mechanical stress. ESR (equivalent series resistance), ESL (equivalent series inductance) is small, the most suitable for high frequency operation of the rectifier power supply.

2. FEATURES

- High reliability and stability.
- Higher mechanical endurance.
- Anti thermal stress and mechanical stress.
- Improved vibration performance.
- More capacitance without changing footprint.
- RoHS & HALOGEN Compliant.

3. APPLICATIONS

- DC to DC converter.
- High voltage coupling/DC blocking.
- Back-lighting inverters.
- Snubbers in high frequency power converters.
- Power supplies.
- Surge protection.
- Filtering, smoothing, and decoupling application.

4. HOW TO ORDER

<u>FE</u>	<u>2H</u>	<u>X</u>	<u>106</u>	<u>K</u>	<u>500</u>	<u>L</u>	<u>G</u>	<u>L</u>	<u>M</u>
PDC Family	Size	Dielectric	Capacitance	Tolerance	Rated Voltage	Packaging	Thickness	Control Code	Special Code
Table 1	Table 2	Table 3	Table 4	Table 5	Table 6	Table 7	Table 8	Table 9	Table 10

Table 1 PDC Family	
Code	Description
FE	Stacked Capacitors Series

Table 2 Stack chip quantity and chip size					
The first digit : # of chips in stack					
Second digit code : chip size (below)					
Code	Description	Code	Description	Code	Description
A	1210 (3225)	G	1825 (4563)	I	2225 (5763)
C	1812 (4532)	H	2220 (5750)		

Table 3 Dielectric Material Characteristics			
Code	Description	Code	Description
N	C0G	X	X7R

Table 4 Capacitance Rule Code			
Code	Description	Code	Description
R47	0.47pF	102	102=10x10 ² =1000pF
0R5	0.5pF	104	104=10x10 ⁴ =100nF
100	100=10x10 ⁰ =10pF	106	106=10x10 ⁶ =10μF

Table 5 Tolerance					
Code	Description	Code	Description	Code	Description
A	±0.05 pF	I	-10% ~ 0%	Q	±0.03 pF
B	±0.10 pF	J	±5 %	Z	-20% ~ +80%
C	±0.25 pF	K	±10 %	X	+10% ~ +20%
D	±0.50 pF	L	0% ~ +10%		
F	±1 %	M	±20 %		
G	±2 %	N	-5% ~ +10%		
H	±3 %	P	±0.02 pF		

Table 6 Rated Voltage					
Code	Description	Code	Description	Code	Description
500	50Vdc	251	250Vdc		
101	100Vdc	501	500Vdc		
201	200Vdc	631	630Vdc		

Table 7 Packaging Type			
Code	Description	Code	Description
B	Bulk	T	Tray package
L	Tape and 13" Reel, Embossed Tape		

Table 8 Thickness Description					
Code	Description	Code	Description	Code	Description
A	3.00±0.35 mm	J	7.80±0.35 mm	S	12.60±0.35 mm
B	3.60±0.35 mm	K	8.40±0.35 mm	T	13.20±0.35 mm
C	4.20±0.35 mm	L	9.00±0.35 mm	U	1.70±0.25 mm
D	4.80±0.35 mm	M	9.60±0.35 mm	V	2.10±0.25 mm
E	5.40±0.35 mm	N	10.20±0.35 mm	W	2.50±0.25 mm
F	6.00±0.35 mm	P	10.80±0.35 mm		
G	6.60±0.35 mm	Q	11.40±0.35 mm		
H	7.20±0.35 mm	R	12.00±0.35 mm		

Table 9 Control Code			
Code	Description	Code	Description
L	L type lead	K	K type lead
J	J type lead	B	B type lead
S	Straight type lead	F	Straight type lead

Table 10 Special Code			
Code	Description	Code	Description
Blank	General purpose	M	Automotive

5. EXTERNAL DIMENSIONS



Size Inch (mm)	L (mm)	W (mm)	Code / T (mm)	E (mm)	
1210 (3225)	3.50±0.40	2.50±0.40	Reference Table 8	1.10±0.15	 L Type Lead
1812 (4532)	4.80±0.40	3.20±0.40		1.40±0.15	
1825 (4563)	4.80±0.40	6.30±0.50		1.70±0.15	 L Type Lead
2220 (5750)	6.00±0.50	5.00±0.50		1.70±0.15	
2225 (5763)	6.00±0.50	6.30±0.50		1.70±0.15	

Fig. 5.1 The outline of Stacked Capacitors

6. GENERAL ELECTRICAL DATA

Dielectric	COG	X7R														
Size	1210, 1812, 1825, 2220, 2225	1210, 1812, 1825, 2220, 2225														
Rated voltage (WVDC)	50V, 100V, 200V, 250V, 500V, 630V	50V, 100V, 200V, 250V, 500V, 630V														
Capacitance range	220nF Max.	47µF Max.														
Capacitance tolerance	Reference to Table 5	Reference to Table 5														
Tan δ	<table border="1"> <thead> <tr> <th>Cap. Range</th> <th>Q Spec.</th> </tr> </thead> <tbody> <tr> <td>Cap. <30pF</td> <td>Q≥400+20C</td> </tr> <tr> <td>Cap. ≥30pF</td> <td>Q≥1000</td> </tr> </tbody> </table>	Cap. Range	Q Spec.	Cap. <30pF	Q≥400+20C	Cap. ≥30pF	Q≥1000	<table border="1"> <thead> <tr> <th>Cap. Range</th> <th>D.F. Spec.</th> </tr> </thead> <tbody> <tr> <td>1210≥2.2µF</td> <td>≤5.0%</td> </tr> <tr> <td>1812~2225≥4.7µF</td> <td>≤5.0%</td> </tr> <tr> <td>Other</td> <td>≤2.5%</td> </tr> </tbody> </table>	Cap. Range	D.F. Spec.	1210≥2.2µF	≤5.0%	1812~2225≥4.7µF	≤5.0%	Other	≤2.5%
	Cap. Range	Q Spec.														
	Cap. <30pF	Q≥400+20C														
Cap. ≥30pF	Q≥1000															
Cap. Range	D.F. Spec.															
1210≥2.2µF	≤5.0%															
1812~2225≥4.7µF	≤5.0%															
Other	≤2.5%															
Capacitance & Tan δ Test condition	Measured at the condition of 30~70% related humidity	Measured at the condition of 30~70% related humidity														
	For 25°C at ambient temperature	Preconditioning for Class II MLCC : Perform a heat treatment at 150±10°C for 1 hour, then leave in ambient condition (25°C) for 24±2 hours before measurement														
	<table border="1"> <thead> <tr> <th>Cap. Range</th> <th>Test Condition</th> </tr> </thead> <tbody> <tr> <td>Cap. <1000pF</td> <td>1.0±0.2Vrms, 1.0MHz±10%</td> </tr> <tr> <td>Cap. ≥1000pF</td> <td>1.0±0.2Vrms, 1.0KHz±10%</td> </tr> </tbody> </table>	Cap. Range	Test Condition	Cap. <1000pF	1.0±0.2Vrms, 1.0MHz±10%	Cap. ≥1000pF	1.0±0.2Vrms, 1.0KHz±10%	<table border="1"> <thead> <tr> <th>Cap. Range</th> <th>Test Condition</th> </tr> </thead> <tbody> <tr> <td>Cap. ≤10µF</td> <td>1.0±0.2Vrms, 1.0KHz±10%</td> </tr> <tr> <td>Cap. >10µF</td> <td>0.5±0.2Vrms, 120Hz±20%</td> </tr> </tbody> </table>	Cap. Range	Test Condition	Cap. ≤10µF	1.0±0.2Vrms, 1.0KHz±10%	Cap. >10µF	0.5±0.2Vrms, 120Hz±20%		
Cap. Range	Test Condition															
Cap. <1000pF	1.0±0.2Vrms, 1.0MHz±10%															
Cap. ≥1000pF	1.0±0.2Vrms, 1.0KHz±10%															
Cap. Range	Test Condition															
Cap. ≤10µF	1.0±0.2Vrms, 1.0KHz±10%															
Cap. >10µF	0.5±0.2Vrms, 120Hz±20%															
Insulation resistance at Ur	≥10GΩ or RxC≥500Ω-F, whichever is smaller	≥10GΩ or RxC≥100Ω-F, whichever is smaller														
Operating temperature	-55 to +125°C	-55 to +125°C														
Capacitance characteristic	±30ppm / °C	±15%														
Termination	L / J / Straight type lead	L / J / Straight type lead														

7. CAPACITANCE RANGE (Max.)

7-1. C0G

Dimension	Code	Rated Voltage					
		50V	100V	200V	250V	500V	630V
1210	1A	393	223	103	103	103	103
1812	1C	104	473	273	273	223	223
	2C	224(M)	104	563	563	473(M)	473(M)
1825	1G	104	104	683	683	473	223
	2G	224(M)	224(M)	134	134	104	473(M)
2220	1H	104	104	683	683	473	223
	2H	224(M)	224(M)	134	134	104	473(M)
2225	1I	104	104	104	104	823	683
	2I	224(M)	224(M)	224(M)	224(M)	184(M)	134

7-2. X7R

Dimension	Code	Rated Voltage					
		50V	100V	200V	250V	500V	630V
1210	1A	475	335	684	684	104	104
1812	1C	106	475	105	105	474	224
	2C	226(M)	106	225(M)	225(M)	105	474(M)
1825	1G	106	106	105	105	564	564
	2G	226(M)	226(M)	225(M)	225(M)	125(M)	125(M)
2220	1H	226	106	225	225	474	474
	2H	476(M)	226(M)	475(M)	475(M)	105	105
2225	1I	106	106	275	275	564	564
	2I	226(M)	226(M)	565	565	125(M)	125(M)

(M) means M tolerance only.

7-3. Customizable, Please contact the liaison.



8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																		
1.	Visual and Dimensions	---	* No remarkable defect. * Dimensions to confirm to individual specification sheet.																		
2.	Capacitance		* Shall not exceed the limits given in the detailed spec.																		
3.	Q/D.F. (Dissipation Factor)	* Class I : Cap.≤1000pF, 1.0±0.2Vrms, 1MHz±10%. Cap.>1000pF, 1.0±0.2Vrms, 1KHz±10%.	<table border="1"> <thead> <tr> <th>Dielectric</th> <th>Cap. Range</th> <th>Q/D.F.</th> </tr> </thead> <tbody> <tr> <td rowspan="2">Class I (C0G)</td> <td>Cap.≥30pF</td> <td>Q≥1000</td> </tr> <tr> <td>Cap.<30pF</td> <td>Q≥400+20C</td> </tr> <tr> <td rowspan="2">Class II (X7R)</td> <td>1210≥2.2μF & 1812~2220≥4.7μF</td> <td>D.F.≤5.0%</td> </tr> <tr> <td>Other</td> <td>D.F.≤2.5%</td> </tr> </tbody> </table>	Dielectric	Cap. Range	Q/D.F.	Class I (C0G)	Cap.≥30pF	Q≥1000	Cap.<30pF	Q≥400+20C	Class II (X7R)	1210≥2.2μF & 1812~2220≥4.7μF	D.F.≤5.0%	Other	D.F.≤2.5%					
		Dielectric	Cap. Range	Q/D.F.																	
Class I (C0G)	Cap.≥30pF	Q≥1000																			
	Cap.<30pF	Q≥400+20C																			
Class II (X7R)	1210≥2.2μF & 1812~2220≥4.7μF	D.F.≤5.0%																			
	Other	D.F.≤2.5%																			
		* Class II : Cap.≤10μF, 1.0±0.2Vrms, 1KHz±10%. Cap.>10μF, 0.5±0.2Vrms, 120Hz±20%.																			
4.	Temperature Coefficient	* With no electrical load.																			
		<table border="1"> <thead> <tr> <th>T.C.</th> <th>Operating Temp.</th> </tr> </thead> <tbody> <tr> <td>C0G</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X7R</td> <td>-55~125°C at 25°C</td> </tr> </tbody> </table>	T.C.	Operating Temp.	C0G	-55~125°C at 25°C	X7R	-55~125°C at 25°C	<table border="1"> <thead> <tr> <th>T.C.</th> <th>Capacitance Change</th> </tr> </thead> <tbody> <tr> <td>C0G</td> <td>Within ±30ppm/°C</td> </tr> <tr> <td>X7R</td> <td>Within ±15%</td> </tr> </tbody> </table>	T.C.	Capacitance Change	C0G	Within ±30ppm/°C	X7R	Within ±15%						
T.C.	Operating Temp.																				
C0G	-55~125°C at 25°C																				
X7R	-55~125°C at 25°C																				
T.C.	Capacitance Change																				
C0G	Within ±30ppm/°C																				
X7R	Within ±15%																				
5.	Insulation Resistance	<table border="1"> <thead> <tr> <th>Rated Vol. (V)</th> <th>Apply Voltage</th> <th>Test Time</th> </tr> </thead> <tbody> <tr> <td>≤100</td> <td>1 times of UR</td> <td>Max. 120 sec.</td> </tr> <tr> <td>100<V≤500</td> <td>1 times of UR</td> <td>60 sec.</td> </tr> <tr> <td>>500</td> <td>500Vdc</td> <td>60 sec.</td> </tr> </tbody> </table>	Rated Vol. (V)	Apply Voltage	Test Time	≤100	1 times of UR	Max. 120 sec.	100<V≤500	1 times of UR	60 sec.	>500	500Vdc	60 sec.	<table border="1"> <thead> <tr> <th>Dielectric</th> <th>Requirements</th> </tr> </thead> <tbody> <tr> <td>Class I</td> <td>≥10GΩ or RxC≥500Ω-F, whichever is smaller</td> </tr> <tr> <td>Class II</td> <td>≥10GΩ or RxC≥100Ω-F, whichever is smaller</td> </tr> </tbody> </table>	Dielectric	Requirements	Class I	≥10GΩ or RxC≥500Ω-F, whichever is smaller	Class II	≥10GΩ or RxC≥100Ω-F, whichever is smaller
		Rated Vol. (V)	Apply Voltage	Test Time																	
≤100	1 times of UR	Max. 120 sec.																			
100<V≤500	1 times of UR	60 sec.																			
>500	500Vdc	60 sec.																			
Dielectric	Requirements																				
Class I	≥10GΩ or RxC≥500Ω-F, whichever is smaller																				
Class II	≥10GΩ or RxC≥100Ω-F, whichever is smaller																				
6.	Dielectric Strength	<table border="1"> <thead> <tr> <th>Rated Voltage</th> <th>Condition</th> </tr> </thead> <tbody> <tr> <td>≤100</td> <td>2.5 times of UR</td> </tr> <tr> <td>100<V≤250</td> <td>2.0 times of UR</td> </tr> <tr> <td>250<V≤500</td> <td>1.5 times of UR</td> </tr> <tr> <td>=630</td> <td>1.2 times of UR</td> </tr> </tbody> </table>	Rated Voltage	Condition	≤100	2.5 times of UR	100<V≤250	2.0 times of UR	250<V≤500	1.5 times of UR	=630	1.2 times of UR	* No evidence of damage or flash over during test.								
		Rated Voltage	Condition																		
≤100	2.5 times of UR																				
100<V≤250	2.0 times of UR																				
250<V≤500	1.5 times of UR																				
=630	1.2 times of UR																				
		* Duration : 1 to 5 sec. * Charge and discharge current less than 50mA.																			
7.	Temperature Cycle	* Conduct the 100 cycles according to the temperatures and time.																			
		<table border="1"> <thead> <tr> <th>Step</th> <th>Temp.(°C)</th> <th>Time(min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30±3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30±3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table>	Step	Temp.(°C)	Time(min.)	1	Min. operating temp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	* No remarkable damage. * Cap. change : C0G Within ±2.5% or ±0.25pF, whichever is larger. X7R Within ±7.5%. * Q/D.F. : C0G : Q≥100% of initial requirement. X7R : D.F.≤150% of initial requirement. * I.R. : To meet the initial requirement.			
Step	Temp.(°C)	Time(min.)																			
1	Min. operating temp. +0/-3	30±3																			
2	Room temp.	2~3																			
3	Max. operating temp. +3/-0	30±3																			
4	Room temp.	2~3																			
		* Before initial measurement (Class II only) : To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).																			
8.	Humidity (Damp Heat) Steady State	* Test temp. : 40±2°C.	* No remarkable damage.																		
		* Humidity : 90~95%RH. * Test time : 500 +24/-0hrs. * Before initial measurement (Class II only) : To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	* Cap. change : C0G Within ±5.0% or ±0.5pF, whichever is larger. X7R Within ±12.5%. * Q/D.F. : C0G : Q≥350. X7R : D.F.≤200% of initial requirement. * I.R. (Class I): : ≥1GΩ or RxC≥50Ω-F, whichever is smaller. * I.R. (Class II): : ≥1GΩ or RxC≥10Ω-F, whichever is smaller.																		

8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																																															
9.	Humidity (Damp Heat) Load	<p>* Test temp. : 40±2°C. * Humidity : 90~95%RH. * Test time : 500 +24/-0hrs. * To apply voltage : Rated voltage (500V max.). * Before initial measurement (Class II only) : To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).</p>	<p>* No remarkable damage. * Cap. change : C0G Within ±7.5% or ±0.75pF, whichever is larger. X7R Within ±12.5%. * Q/D.F. : C0G : Q≥200. X7R : D.F.≤200% of initial requirement. * I.R. : ≥500MΩ or RxC≥25Ω-F, whichever is smaller.</p>																																															
10.	High Temperature Load (Endurance)	<p>* Test temp. : 125±3°C. * To apply voltage :</p> <table border="1"> <thead> <tr> <th>Dielectric</th> <th>Rated Vol.(V)</th> <th>Apply Voltage</th> </tr> </thead> <tbody> <tr> <td rowspan="3">C0G/X7R</td> <td>≤100</td> <td>2.0 times of U_R</td> </tr> <tr> <td>200≤V≤ 500</td> <td>1.5 times of U_R</td> </tr> <tr> <td>=630</td> <td>1.2 times of U_R</td> </tr> </tbody> </table> <p>* Exception items (X7R only) :</p> <p>(1) 150% of rated voltage for below range :</p> <table border="1"> <thead> <tr> <th>Rated Vol.(V)</th> <th>Size</th> <th>Cap. Range</th> </tr> </thead> <tbody> <tr> <td>ALL</td> <td>ALL</td> <td>Cap.≥106</td> </tr> <tr> <td rowspan="5">50V & 100V</td> <td>1210</td> <td rowspan="5">Cap.≥105</td> </tr> <tr> <td>1812</td> </tr> <tr> <td>1825</td> </tr> <tr> <td>2220</td> </tr> <tr> <td>2225</td> </tr> </tbody> </table> <p>(2) 120% of rated voltage for below range :</p> <table border="1"> <thead> <tr> <th>Size</th> <th>Dielectric</th> <th>Rated Voltage</th> <th>Capacitance</th> </tr> </thead> <tbody> <tr> <td>2220</td> <td>X7R</td> <td>≥100V</td> <td>Cap.≥15μF</td> </tr> </tbody> </table> <p>(3) 100% of rated voltage for below range :</p> <table border="1"> <thead> <tr> <th>Size</th> <th>Dielectric</th> <th>Rated Voltage</th> <th>Capacitance</th> </tr> </thead> <tbody> <tr> <td>1206</td> <td>X7R</td> <td>≥100V</td> <td>Cap.≥2.2μF</td> </tr> <tr> <td>1210</td> <td>X7R</td> <td>≥100V</td> <td>Cap.≥3.3μF</td> </tr> <tr> <td>2220</td> <td>X7R</td> <td>≥100V</td> <td>Cap.≥22μF</td> </tr> </tbody> </table> <p>* Test time : 1000 +24/-0 hrs. * Before initial measurement (Class II only) : To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).</p>	Dielectric	Rated Vol.(V)	Apply Voltage	C0G/X7R	≤100	2.0 times of U _R	200≤V≤ 500	1.5 times of U _R	=630	1.2 times of U _R	Rated Vol.(V)	Size	Cap. Range	ALL	ALL	Cap.≥106	50V & 100V	1210	Cap.≥105	1812	1825	2220	2225	Size	Dielectric	Rated Voltage	Capacitance	2220	X7R	≥100V	Cap.≥15μF	Size	Dielectric	Rated Voltage	Capacitance	1206	X7R	≥100V	Cap.≥2.2μF	1210	X7R	≥100V	Cap.≥3.3μF	2220	X7R	≥100V	Cap.≥22μF	<p>* No remarkable damage. * Cap. change : C0G Within ±3.0% or ±0.3pF, whichever is larger. X7R Within ±12.5%. * Q/D.F. : C0G : Q≥350. X7R : D.F.≤200% of initial requirement. * I.R. (Class I) : ≥1GΩ or RxC≥50Ω-F, whichever is smaller. * I.R. (Class II) : ≥1GΩ or RxC≥10Ω-F, whichever is smaller.</p>
Dielectric	Rated Vol.(V)	Apply Voltage																																																
C0G/X7R	≤100	2.0 times of U _R																																																
	200≤V≤ 500	1.5 times of U _R																																																
	=630	1.2 times of U _R																																																
Rated Vol.(V)	Size	Cap. Range																																																
ALL	ALL	Cap.≥106																																																
50V & 100V	1210	Cap.≥105																																																
	1812																																																	
	1825																																																	
	2220																																																	
	2225																																																	
Size	Dielectric	Rated Voltage	Capacitance																																															
2220	X7R	≥100V	Cap.≥15μF																																															
Size	Dielectric	Rated Voltage	Capacitance																																															
1206	X7R	≥100V	Cap.≥2.2μF																																															
1210	X7R	≥100V	Cap.≥3.3μF																																															
2220	X7R	≥100V	Cap.≥22μF																																															

8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements						
11.	Adhesive Strength of Termination	<p>* Capacitors mounted on a substrate. A force of 10N applied perpendicular to the place of substrate and parallel the line joining the center of terminations for 10±1 second.</p>  <p>Capacitor P.C. Board Pressurizing force</p>	<p>* No remarkable damage or removal of the terminations.</p>						
12.	Bending Test	<p>* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1mm per second until the deflection becomes 5mm.</p>  <p>Unit : mm</p>	<p>* No remarkable damage.</p> <table border="1"> <thead> <tr> <th>Dielectric</th> <th>Cap. Change</th> </tr> </thead> <tbody> <tr> <td>C0G</td> <td>Within ±3.0% or ±2.0pF, whichever is larger</td> </tr> <tr> <td>X7R</td> <td>Within ±12.5%</td> </tr> </tbody> </table> <p>(This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test)</p>	Dielectric	Cap. Change	C0G	Within ±3.0% or ±2.0pF, whichever is larger	X7R	Within ±12.5%
Dielectric	Cap. Change								
C0G	Within ±3.0% or ±2.0pF, whichever is larger								
X7R	Within ±12.5%								
13.	Vibration Resistance	<p>* Vibration frequency : 10~55 Hz/min.</p> <p>* Total amplitude : 1.5mm.</p> <p>* Test time : 6 hrs. (Two hrs each in three mutually perpendicular directions)</p> <p>* Before initial measurement (Class II only) : To apply de-aging at 150°C for 1hr then set for 24±2 hrs at room temp.</p> <p>* Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).</p>	<p>* No remarkable damage.</p> <p>* Cap. change and D.F. : To meet initial spec.</p>						

9. PACKAGE DIMENSION AND QUANTITY

9.1. PACKAGE QUANTITY

PDC Family & Size	Thickness (mm)	Plastic tape
		13" reel
FE1A	ALL	1.5k
FE1C	ALL	1.5k
FE2C	ALL	0.5k
FE1H	ALL	1k
FE2H	ALL	0.5k

For other chip size, please contact the liaison

9.2. EMBOSSED TAPE DIMENSIONS




Fig. 9.1 The dimension of plastic tape

Size	FE1A	FE1C	FE2C	FE1H	FE2H
Chip Thickness	3.00±0.35	3.60±0.35	6.00±0.35 6.60±0.35	3.60±0.35 4.20±0.35	6.00±0.35 6.60±0.35
W	12.00±0.30	16.00±0.30	16.00±0.30	16.00±0.30	16.00±0.30
E	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	5.50±0.10	7.50±0.10	7.50±0.10	7.50±0.10	7.50±0.10
P	8.00±0.10	8.00±0.10	12.00±0.10	12.00±0.10	12.00±0.10
P ₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP ₀	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20
P ₂	2.00±0.10	2.00±0.10	2.00±0.10	2.00±0.10	2.00±0.10
D ₀	Ø1.50 +0.10/-0	Ø1.50 +0.10/-0	Ø1.50 +0.10/-0	Ø1.50 +0.10/-0	Ø1.50 +0.10/-0
T	0.40±0.05	0.40±0.05	0.40±0.05	0.40±0.05	0.50±0.05
A ₀	3.00±0.10	3.52±0.10	5.70±0.10	5.70±0.10	5.60±0.10
B ₀	3.82±0.10	5.08±0.10	6.60±0.10	6.45±0.10	6.60±0.10
K ₀	3.40±0.10	3.14±0.10	7.00±0.10	3.75±0.10	7.00±0.10
Unit :	mm	mm	mm	mm	mm

* For other chip size, please contact the liaison.

9. PACKAGE DIMENSION AND QUANTITY

9.3. REEL DIMENSIONS

Reel size	13"	
A	330.0±0.50mm	
B	2.00±0.50mm	
C	13.00+0.50/-0.20mm	
T	2.00+0.50/-0.20 mm	

Fig. 9.2 The dimension of reel

10. FOOTPRINT DIMENSIONS

Size	1210	1812	1825	2220	2225	Fig. 10.1 Illustration of Footprint
D1	4.90	6.80	6.80	8.40	8.40	<p>Dimensions in millimeters</p>
D2	1.40	1.60	1.60	2.20	2.20	
D3	2.10	3.60	3.60	4.00	4.00	
D4	1.40	1.60	1.60	2.20	2.20	
D5	2.80	3.80	6.80	5.50	6.80	

11. APPLICATION NOTES

STORAGE

To prevent the damage of solderability of terminations, the following storage conditions are recommended :

Indoors under 5 ~ 40°C and 20% ~ 70% RH.

No harmful gases containing sulfuric acid, ammonia, hydrogen sulfide or chlorine.

Packaging should not be opened until the capacitors are required for use. If opened, the pack should be re-sealed as soon as is practicable. Taped product should be stored out of direct sunlight, which might promote deterioration in tape or adhesion performance. The product is recommended to be used within 12 months after shipment and checked the solderability before use.

HANDLING

Chip capacitors are dense, hard, brittle, and abrasive materials. They are liable to suffer mechanical damage, in the form of cracks or chips. Chip Capacitors should be handled with care to avoid contamination or damage. To use vacuum or plastic tweezers to pick up or plastic tweezers is recommended for manual placement. Tape and reeled packages are suitable for automatic pick and placement machine.


PREHEAT

In order to minimize the risk of thermal shock during soldering, a carefully controlled preheat is required. The rate of preheat should not exceed 3°C per second.

SOLDERING

Use mildly activated rosin fluxes do not use activated flux. The amount of solder in each solder joint should be controlled to prevent the damage of chip capacitors caused by the stress between solder, chips, and substrate.

a.) Reflow soldering :



COOLING

After soldering, cool the chips and the substrate gradually to room temperature. Natural cooling in air is recommended to minimize stress in the solder joint.

CLEANING

All flux residues must be removed by using suitable electronic-grade vapor-cleaning solvents to eliminate contamination that could cause electrolytic surface corrosion. Good results can be obtained by using ultrasonic cleaning of the solvent. The choice of the proper system is depends upon many factors such as component mix, flux, and solder paste and assembly method. The ability of the cleaning system to remove flux residues and contamination from under the chips is very important.